

MDF FIRE X CARB2/TSCA

Medium density fiberboard with improved fire behavior for use in dry conditions

DESCRIPTION

Sonae Arauco MDF FIRE X CARB2/TSCA is a medium density fibreboard for interior use, with improved fire reaction behaviour. MDF FIRE X CARB2/TSCA has low formaldehyde emission, is certified according to the rules of the official California Air Resources Board (CARB) and compliant with limit of ChemVerbotsV (E05).

Regarding reaction to fire and in accordance with EN13986, MDF FIRE X CARB2/TSCA is classified as B-s2, d0 (Euroclass definition according to EN 13501-1) and it is recommended for use in sectors with strict regulations on the fire performance of the materials used.

The use of MDF FIRE X CARB2/TSCA contributes to reduce the combustion of an element, the spread of fire, the possible heat emissions after the combustion and to prevent or delay the spread of fire to neighbouring elements.

In addition to technical performance MDF FIRE X CARB2/TSCA panels are sustainable and environmental friendly products.

Please check offer & service brochure for information on sizes and thicknesses available.

APPLICATIONS

MDF FIRE X CARB2/TSCA is suitable for public buildings or any space subject to specific fire safety regulations (shopping centres, hospitals, schools, showrooms & hotels). It can be used for covering of walls and ceilings, doors, stands and other applications in the interior.

Due to the wood fibres used in its production, the product has homogeneous faces. The density of the faces also allows the use of a wide range of finishing techniques - lacquering, melamine paper coating, wood sheet or finish foil. Fireproofed in the mass, the product maintains its behaviour of reaction to the fire after cutting and machining.

RECOMMENDATIONS

Boards must be stacked on a hard, level surface and protected from direct contact with water. Expansion and contraction in wood products is directly related to moisture content and must be considered during design and construction; MDF FIRE X CARB2/TSCA panels must be conditioned in the work environment for two to three days before being processed.

When choosing a coating system, it should be confirmed with the manufacturer that it will not adversely affect the Fire Reaction classification of the MDF panel.

Additives added during the production of this product, in exceptional cases, may interfere with certain types of adhesives and lacquers, therefore a test must be carried out before its application.

Wood based panels are biodegradable and can be recycled, follow local regulation for the disposal of residues.

PROPERTIES



VERSATILITY



FIRE RETARDANT



EPA TSCA TITLE VI & CARB 2 CERTIFIED



COMPLIANT WITH CHEMVERBOTS V (E05)



OFFICES & EDUCATION



SPORTS & LEISURE



RESTAURANTS & HOTELS



HEALTH & WELLNESS



RETAIL & EXHIBITIONS



DOORS



PANELING



CONSTRUCTION

MDF FIRE X CARB2/TSCA

Medium density fiberboard with improved fire behavior for use in dry conditions

GENERAL CHARACTERISTICS

PROPERTY	TEST	UNIT	THICKNESS RANGE (mm)		
			10 - 12	>12 - 19	>19 - 30
Tolerance on thickness	EN 324-1	mm	± 0,2	± 0,2	± 0,3
Tolerance on length and width	EN 324-1	mm/m	± 2	± 2	± 2
Edge straightness tolerance	EN 324-2	mm/m	≤ 1,5	≤ 1,5	≤ 1,5
Squareness tolerance	EN 324-2	mm/m	≤ 2	≤ 2	≤ 2
Tolerance on mean density	EN 323	%	± 7	± 7	± 7
Moisture content	EN 322	%	4 - 11	4 - 11	4 - 11

TECHNICAL INFORMATION

PROPERTY	TEST	UNIT	THICKNESS RANGE (mm)		
			10 - 12	>12 - 19	>19 - 30
Density*	EN 323	Kg/m ³	830	800	800
Bending strength	EN 310	N/mm ²	≥ 22	≥ 20	≥ 18
Modulus of elasticity	EN 310	N/mm ²	≥ 2500	≥ 2200	≥ 2100
Internal bond	EN 319	N/mm ²	≥ 0,60	≥ 0,55	≥ 0,55
Thickness swelling 24 hours	EN 317	%	≤ 15	≤ 12	≤ 10
Formaldehyde emission class	CARB Phase 2 / EPA TSCA**				

* Value to be used only as a reference

**compliant with limit of ChemVerbotsV (E05)

MDF FIRE X CARB2/TSCA meets the specification of EN 622-5, type MDF, and is CE marked. For more information regarding the technical properties, please check the product Declaration of Performance (DoP).

CERTIFICATIONS

Please pay attention to certified products:



The mark of
responsible forestry
FSC® C009049



FSC® and PEFC™ -certified products are available on request and availability.

www.sonaearauco.com

TDS.03.46.SAD.R01

All the product names and company names used in this data sheet are trade names and / or registered trademarks belonging to the respective proprietors. Any reproduction requires the express authorization of Sonae Arauco and / or the respective trademark proprietor. Sonae Arauco assumes no liability for any possible errors in this data sheet. This technical data sheet reflects the current technical specifications at the time of print and will be superseded by any new edition. The Company reserves the right to change specifications at any time without prior notification. Our detailed instructions for use must be observed. The respective building regulations must be complied with. It is important to check the material's suitability for the intended purpose.