

CORE&TECHNICAL

Products

MDF HYDRO X CARB2/TSCA

Medium density fiberboard for use in humid conditions

DESCRIPTION

Sonae Arauco MDF HYDRO X CARB2/TSCA is a moisture resistant board for general purposes, indicated for applications in humid conditions (EN 622-5, type MDF.H). MDF HYDRO X CARB2/TSCA has low formaldehyde emission, is certified according to the rules of the official California Air Resource Board (CARB) and compliant with limit of ChemVerbotsV (E05).

Regarding reaction to fire and according to EN 13986, MDF HYDRO X CARB2/TSCA, with a thickness ≥ 9 mm, is classified as D-s2, d0 (Euroclass definition by EN 13501-1).

In addition to technical performance MDF HYDRO X panels are sustainable and environmental friendly products.

Please check offer & service brochure for information on sizes and thicknesses available.

APPLICATIONS

MDF HYDRO X CARB2/TSCA is the best choice for use in areas with a temporary high humidity environment. Due to the wood fibres and special resins used in its production, the product presents a very good dimensional stability and low swelling.

The density of surfaces also gives the possibility of using a wide range of finishing techniques: lacquering, coating, veneering, foil wrapping and covering. Ideal for manufacturing kitchen and bathroom furniture, doors and windows sills and other interior applications when is expected higher levels of humidity.

RECOMMENDATIONS

Boards must be stacked on a hard, level surface and protected from direct contact with water. Expansion and contraction in wood products is directly related to moisture content and must be considered during design and construction.

Pigments added during manufacturing of this product in exceptional cases may interfere with certain types of adhesives, a test before you apply them should therefore be conducted.

Wood based panels are biodegradable and can be recycled, follow local regulation for the disposal of residues.

PROPERTIES



VERSATILITY



EASY TO MILL



DIMENSIONAL
STABILITY



MOISTURE
RESISTANT



EPA TSCA TITLE VI &
CARB 2 CERTIFIED



COMPLIANT WITH
CHEMVERBOTSV



KITCHENS



BATHROOMS



RESTAURANTS &
HOTELS



HEALTH & WELLNESS



DOORS



CONSTRUCTION

MDF HYDRO X CARB2/TSCA

Medium density fiberboard for use in humid conditions

GENERAL CHARACTERISTICS

PROPERTY	TEST	UNIT	THICKNESS RANGE (mm)				
			8 - 9	>9 - 12	>12 - 19	>19 - 30	>30 - 40
Tolerance on thickness	EN 324-1	mm	± 0,2	± 0,2	± 0,2	± 0,3	± 0,3
Tolerance on length and width	EN 324-1	mm/m	± 2	± 2	± 2	± 2	± 2
Edge straightness tolerance	EN 324-2	mm/m	≤ 1,5	≤ 1,5	≤ 1,5	≤ 1,5	≤ 1,5
Squareness tolerance	EN 324-2	mm/m	≤ 2	≤ 2	≤ 2	≤ 2	≤ 2
Tolerance on mean density	EN 323	%	± 7	± 7	± 7	± 7	± 7
Moisture content	EN 322	%	4 - 11	4 - 11	4 - 11	4 - 11	4 - 11

TECHNICAL INFORMATION

PROPERTY	TEST	UNIT	THICKNESS RANGE (mm)				
			8 - 9	>9 - 12	>12 - 19	>19 - 30	>30 - 40
Density *	EN 323	Kg/m ³	770	765	765	755	745
Bending strength	EN 310	N/mm ²	≥ 34	≥ 32	≥ 30	≥ 26	≥ 20
Modulus of elasticity	EN 310	N/mm ²	≥ 3400	≥ 3200	≥ 3000	≥ 2600	≥ 2300
Internal bond	EN 319	N/mm ²	≥ 1,00	≥ 0,90	≥ 0,80	≥ 0,80	≥ 0,70
Thickness swelling 24 hours	EN 317	%	≤ 11	≤ 9	≤ 7	≤ 6	≤ 6
Internal bond after cyclic test	EN 321	N/mm ²	≥ 0,30	≥ 0,25	≥ 0,20	≥ 0,15	≥ 0,10
Swelling after cyclic test	EN 321	%	≤ 19	≤ 16	≤ 15	≤ 15	≤ 15
Formaldehyde emission class	CARB Phase 2 / EPA TSCA **						

* Value to be used only as a reference
 **compliant with limit of ChemVerbotsV (E05)

MDF HYDRO X CARB2/TSCA boards meet the specifications of EN 622-5, type MDF.H, and are CE marked. For more information regarding the technical properties, please check the product Declaration of Performance (DoP).

CERTIFICATIONS

Please pay attention to certified products:



The mark of responsible forestry
 FSC® C009049



FSC® and PEFC™ -certified products are available on request and availability.

www.sonaearauco.com

TDS.03.42.SAD.R02

All the product names and company names used in this data sheet are trade names and / or registered trademarks belonging to the respective proprietors. Any reproduction requires the express authorization of Sonae Arauco and / or the respective trademark proprietor. Sonae Arauco assumes no liability for any possible errors in this data sheet. This technical data sheet reflects the current technical specifications at the time of print and will be superseded by any new edition. The Company reserves the right to change specifications at any time without prior notification. Our detailed instructions for use must be observed. The respective building regulations must be complied with. It is important to check the material's suitability for the intended purpose.

**SONAE
 ARAUCO**

Taking wood further