



CORE&TECHNICAL

Products

OSB 2 ECOBOARD

Load-bearing OSB for use in dry conditions

DESCRIPTION

Sonae Arauco OSB 2 ECOBOARD is a structured panel with three layers of long wood strands arranged at right angles to each other, bonded with formaldehyde-free resin applied under high temperature and pressure. In the outer layers, the particles are arranged lengthwise in relation to the length of the board; in the inner layer, they are at right angles to the length of the board. It is a product with excellent mechanical resistance and durability and is extremely versatile.

OSB 2 ECOBOARD panels are governed under building law with characteristic values according to EN 1995-1-1 (Eurocode 5), presenting high strength and stability.

For further information on available sizes and thicknesses, please see our Offer & Service Brochure.

APPLICATIONS

OSB 2 ECOBOARD is a wood-based panel type OSB/2 according to EN 300 and EN 13986 and must be applied in service class 1 (restrictions in temperature and ambient humidity).

The product is suitable for load-bearing ceiling sheathing, floating floor construction, decorative areas in the interior construction, shop fitting and exhibition stand construction.

RECOMMENDATIONS

Boards must be stacked on a hard, level surface and protected from direct contact with water. Expansion and contraction in wood products is directly related to moisture content and must be considered during design and construction.

Wood based panels are biodegradable and can be recycled, follow local regulation for the disposal of residues.

PROPERTIES



VERSATILITY



EASY TO MILL



DURABILITY



COMPLIANT WITH CHEMVERBODSV



LOW EMISSIONS



RETAIL & EXHIBITIONS



PANELLING

OSB 2 ECOBOARD

Load-bearing OSB for use in dry conditions

GENERAL CHARACTERISTICS

PROPERTY	TEST	UNIT	THICKNESS RANGE (mm)		
			6 - 10	>10 - <18	18 - 25
Tolerance on thickness (un-sanded)	EN 324-1	mm	± 0,8	± 0,8	± 0,8
Tolerance on length and width	EN 324-1	mm/m	± 3,0	± 3,0	± 3,0
Edge straightness tolerance	EN 324-2	mm/m	≤ 1,5	≤ 1,5	≤ 1,5
Squareness tolerance	EN 324-2	mm/m	≤ 2	≤ 2	≤ 2
Tolerance on mean density	EN 323	%	± 15	± 15	± 15
Moisture content	EN 322	%	2 - 12	2 - 12	2 - 12

TECHNICAL INFORMATION

PROPERTY	TEST	UNIT	THICKNESS RANGE (mm)		
			6 - 10	>10 - <18	18 - 25
Density*	EN 323	Kg/m ³	> 600	> 600	> 600
Bending strength – major axis	EN 310	N/mm ²	≥ 22	≥ 20	≥ 18
Bending strength – minor axis	EN 310	N/mm ²	≥ 11	≥ 10	≥ 9
Modulus of elasticity – major axis	EN 310	N/mm ²	≥ 3500	≥ 3500	≥ 3500
Modulus of elasticity – minor axis	EN 310	N/mm ²	≥ 1400	≥ 1400	≥ 1400
Internal bond	EN 319	N/mm ²	≥ 0,34	≥ 0,32	≥ 0,30
Swelling (24 hours)	EN 317	%	≤ 20	≤ 20	≤ 20
Formaldehyde emission class				E1**	

* Value to be used only as a reference

** Compliant with limit of ChemVerbotsV (E05)

OSB 2 ECOBOARD boards meet the specifications of EN 300, type OSB/2, and are CE marked. For more information regarding the technical properties check de Product Declaration of Performance (DoP).

CERTIFICATIONS

Please pay attention to certified products:



The mark of responsible forestry
FSC® C009049



FSC® and PEFC™ - certified products are available on request and availability.

www.sonaearauco.com

TDS.01.01.SA.R02

All the product names and company names used in this data sheet are trade names and / or registered trademarks belonging to the respective proprietors. Any reproduction requires the express authorization of Sonae Arauco and /or the respective trademark proprietor. Sonae Arauco assumes no liability for any possible errors in this data sheet. This technical data sheet reflects the current technical specifications at the time of print and will be superseded by any new edition. The Company reserves the right to change specifications at any time without prior notification. Our detailed instructions for use must be observed. The respective building regulations must be complied with. It is important to check the material's suitability for the intended purpose.

OSB 2 ECOBOARD

Load-bearing OSB for use in dry conditions

ADDITIONAL INFORMATION

PROPERTY	UNIT	THICKNESS (mm)	BENDING f_m		TENSION f_t		COMPRESSION f_c		PANEL SHEAR f_v	PANEL SHEAR f_v
			or 0	⊥ or 90	or 0	⊥ or 90	or 0	⊥ or 90		
Strength	N/mm ²	6 – 10	18,0	9,0	9,9	7,2	15,9	12,9	6,8	1,0
		> 10 – 18	16,4	8,2	9,4	7,0	15,4	12,7		
		> 18 – 25	14,8	7,4	9,0	6,8	14,8	12,4		

PROPERTY	UNIT	THICKNESS (mm)	BENDING E_m		TENSION E_t		COMPRESSION E_c		PANEL SHEAR G_v	PANEL SHEAR G_v
			or 0	⊥ or 90	or 0	⊥ or 90	or 0	⊥ or 90		
Stiffness	N/mm ²	6 – 25	4930	1980	3800	3000	3800	3000	1080	50